

Biresin® G28 PUR - Vacuum Casting resin

Areas of Application

- Manufacture of temperature resistant housings, coverings and other mouldings
- Manufacture of thinwalled parts with complex structure

Product Benefits

- Simulation of PE/PP and ABS
- With hardener **Biresin® G53** for higher strength and faster curing
- With hardener **Biresin® U5** for higher temperature resistance
- Dyeable with **Biresin®-Farbpasten**
- Can be cured at RT

Description

- Basis Two-component-PUR-system
- Resin **Biresin® G28**, polyol, beige, unfilled
- Hardener **Biresin® G53**, MDI-based isocyanate, amber, unfilled
- Hardener **Biresin® U5**, MDI-based isocyanate, brown, unfilled

Processing Data		Resin	Hardener	
Individual components		Biresin® G28	Biresin® G53	Biresin® U5
Viscosity, 25°C	mPas	approx. 50	approx. 175	approx. 110
Density	g/cm³	1.00	1.23	1.23
Mixing ratio resin to hardener	in pbw	100	75	67
Mixtures				
Mixed viscosity, 25°C	mPas		approx. 150	approx. 120
Potlife, 200 g, RT	min		4	5
Demoulding time, RT	min		60 - 90	60 - 90
Curing time, RT	d		3	3

Physical Data (approx.-values)

Biresin® G28 resin		to hardener	Biresin® G53	Biresin® U5
Colour			beige	
Density	ISO 1183	g/cm³	1.1	1.1
Shore hardness	ISO 868	-	D 79	D 79
E-Modulus	ISO 178	MPa	1,610	1,490
Flexural strength	ISO 178	MPa	72	67
Tensile strength	ISO 527	MPa	47	40
Compressive strength	ISO 604	MPa	60*	56*
Impact resistance	ISO 179	kJ/m²	25	25
Heat distortion temperature	ISO 75B	°C	93**	102**

* at 10% compressive strain
** values after post curing: 4 h / 80°C

Packaging

Individual components	Biresin® G28 resin	50 kg; 20 kg; 5 kg net
	Biresin® G53 hardener	20 kg; 10 kg net
	Biresin® U5 hardener	17 kg; 4.25 kg net

Processing

- The material temperature must be 18 - 25°C.
- The resin component must be stirred thoroughly before use.
- Both components must be under vacuum for several minutes before mixing in right mixing ratio and poured into preheated moulds (70°C).
- After complete filling of the moulds, vacuum is switched off and moulds are placed in an oven at 70°C for curing until demoulding.

Storage

- Minimum shelf life is 12 month under room condition (18 - 25°C), when stored in original un-opened containers.
- After prolonged storage at low temperature, crystallisation of components may occur. This is easily removed by warming up for a sufficient time to a maximum of 70°C. Allow to cool to room temperature before use.
- Containers must be closed tightly immediately after use to prevent moisture ingress. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SCABRO
Ideeën Krijgen Vorm

Distributeur voor Nederland, België en Luxemburg: Scabro Composites

Vliegveld Valkenburg Wassenaarseweg 75-3265 NL - 2223 LA Katwijk The Netherlands
Tel: +31 (0) 71 4017246 Fax: +31 (0) 84 7402572 Email: info@scabro.com www.scabro.com