

Biresin[®] HC586

Reaction accelerator for selected Biresin[®]-PUR - resins

Areas of Application

- For reducing of potlife and reaction acceleration of PUR-systems with MDI-curing:
Biresin[®] G46, Biresin[®] G48, Biresin[®] U1305, Biresin[®] 407

Description

- Basis amine based catalyst, low viscosity

Processing Data

Addition amount Biresin[®] HC586 to polyol component	%	without	0,05	0,1	0,2	0,3	0,4	0,5	1,0
		Potlife							
Biresin[®] G46 resin	min	40	20	10	5	3	-	-	-
Biresin[®] G48 resin	min	45-60	-	-	-	10	-	5	-
Biresin[®] U1305 hardener	min	15-20	-	-	-	-	3	-	2
Biresin[®] 407 resin	min	15	-	6	-	3	-	100 s	-

Packaging

Individual components **Biresin[®] HC586** 0.5 kg net

Processing

- Biresin[®] HC586 is to add to the thoroughly homogenised component. Mixtures are stable, but has to be used up as soon as possible.
- Pay attention to the processing conditions of corresponding Biresin[®] resins too.

Storage

- Minimum shelf life is 12 month under room condition (18 - 25°C), when stored in original un-opened containers.
- Containers must be closed water tight immediately after use and prevented from moisture. The residual material has to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling and storage of products, users should refer to the current Safety Data Sheet containing physical, ecological, toxicological and other safety related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SCABRO
Ideeën Krijgen Vorm

Distributeur voor Nederland, België en Luxemburg: Scabro Composites

Vliegveld Valkenburg Wassenaarseweg 75-3265 NL - 2223 LA Katwijk The Netherlands
Tel: +31 (0) 71 4017246 Fax: +31 (0) 84 7402572 Email: info@scabro.com www.scabro.com